



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

**0 190 630
A1**

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 86101028.8

(51) Int. Cl.⁴: A 22 C 13/00

(22) Date of filing: 25.01.86

(30) Priority: 04.02.85 US 697986

(43) Date of publication of application:
13.08.86 Bulletin 86/33

(84) Designated Contracting States:
AT BE CH DE FR GB IT LI LU NL SE

(71) Applicant: Teepak, Inc.
Executive Plaza East Suite 1100 1211 West 22nd Street
Oakbrook Illinois 60521(US)

(72) Inventor: Smith, Burl Lester
R.R. No. 3 Box 199
Danville Illinois 61832(US)

(72) Inventor: Bridgeford, Douglas Joseph
1209 West John Street
Champaign Illinois 61832(US)

(72) Inventor: Pritikin, William Barnett
deseased(US)

(74) Representative: Weber, Dieter, Dr. et al,
Dr. Dieter Weber und Klaus Seiffert Patentanwälte
Gustav-Freytag-Strasse 25 Postfach 6145
D-6200 Wiesbaden 1(DE)

(54) Preserved high moisture, ready-to-stuff food casings.

(57) Packaged fibrous and non-fibrous reinforced food casings containing sufficient water that presoaking prior to stuffing can be eliminated. The casings which rely on water as the sole or principal plasticizer do not rely on chemical type plasticizers like glycerin and propylene glycol. The premoisturized, ready-to-stuff casings are preserved with effective amounts of a high pH active antimycotic agent. Drying requirements can be reduced or eliminated.

EP 0 190 630 A1

PRESERVED, HIGH MOISTURE, READY-TO-STUFF
FOOD CASINGS

BACKGROUND OF THE INVENTION

The present invention relates generally to ready-to-stuff type food casings having sufficient moisture content that further moisture need not be added prior to stuffing. The invention especially relates to such casings which contain an antimycotic agent to prevent spoilage of the food casing prior to use.

Food casings, and more particularly, sausage casings like those made of regenerated cellulose and collagen have been widely used for years in processing frankfurters, sausages, bologna, salamis, etc. Tubular casings of regenerated cellulose, for example, are manufactured by extruding viscose into a fibrous web which is then regenerated in a coagulating bath. The regenerated gel casing is washed and plasticized usually in a glycerin containing bath. The plasticized gel film is inflated and passed through lengthy gas fueled hot-air dryers where the moisture content of the casing is reduced to a relatively low level, e.g. 5 to 10 percent. The dried casings may be shirred into tightly compressed strands and packaged. They may be stored for indefinite time periods or shipped to meat processing plants for stuffing at some later time. Before being used by meat processors the tubular strands or flat large size casings are customarily soaked in water to increase their moisture content usually to 30 to 55 percent on an "as is" basis (total casing

weight). The extra moisture imparts additional plasticization and flexibility to withstand high speed stuffing without tearing and permits tubular shirred strands to extend smoothly without breaking.

The foregoing protocol, relating to plasticized and dried cellulosic casings, ordinarily does not present special problems with regard to preservation from molds, yeasts and bacteria developing during storage. This is true because such casings contain from 18-25 percent by weight glycerin and/or propylene glycol which in addition to being plasticizers incidentally impart microbicidal properties to the casing. In addition, by maintaining relatively low moisture levels during packaging and storage, conditions favoring germination of microbes are minimized.

However, with the advent of newer automated meat processing equipment, there has been greater emphasis on stuffing operations where pre-soaking procedures for casings at the meat packing plant are totally eliminated. Therefore, with greater frequency, casings are being supplied to food processors as ready-to-stuff shirred strands and flat reelstock, particularly where large size casings are used for salamis, bologna, meatloaves, cooked and smoked ham butts, etc. Because of the relatively high moisture levels of ready-to-stuff type casings, bacteria, yeasts and molds, can form on the casings during storage.

Where such casings are regenerated cellulose they have been manufactured as previously described, except after addition of a

plasticizer such as glycerin, the casing is dried and then remoisturized.

It was not uncommon to find the practice of drying after addition of plasticizer, to allow other process steps. For instance, printing on casing sidewalls or for application of peeling aids or to reduce the moisture content to a level thought more conducive for shirring. As a final step however, much of the water previously removed by driers was then added back to the casings in order to place the casings in ready-to-stuff condition. Accordingly, previous ready-to-stuff type casings were mainly dependent on relatively high concentrations of costly chemical type plasticizers as primary plasticizers which incidentally also inhibited the development of microbes.

Such high concentrations of chemical type plasticizers however, may pose a potential indirect health hazard. Those casings containing such high levels of propylene glycol, glycerin and other similar type materials may in some instances diffuse from the casing sidewall into the surface of the encased meat product after stuffing. The level of antimycotic agent present although relatively high, would not prevent spoilage throughout the packaged meat product, but could mask visual evidence of meat spoilage and deterioration typically manifested by the appearance of sliming, souring or greening formation on the surface. Accordingly, such high levels of polyols added to food casings primarily as plasticizers may block the natural indicators of food spoilage which are necessary for consumer safety.

Premoisturized, ready-to-stuff type casings relying on high levels of chemical type preservatives and primary plasticizers are described in the following patents:

U.S. 1,868,203 discloses a process for preparing natural type sausage casings by treating in a 20 percent solution of glycerin and water. The casings can be immediately filled with meat or dried to remove moisture and stored for indefinite periods without deterioration. U.S. 2,802,744 discloses premoisturized, ready-to-stuff alginic acid or alginate sausage casings which may have water contents of 150 percent. 15 to 40 percent glycerin may be added onto the casing as a plasticizer. Such casings can be packaged in polyethylene bags and stored.

U.S. 3,617,312 discloses a polymeric water insoluble overcoating for dry sausage casings containing an antimycotic agent which slowly leaches from the overcoating after the casing is stuffed with meat emulsion. These casings were not premoisturized and packaged and required an additional water insoluble polymer such as a polyester or polyacrylic. Furthermore, the antimycotic agent was primarily in the overcoating rather than throughout the casing. The antimycotic agents incorporated into the water insoluble polymer could include, among many others, lower alkyl esters of p-hydroxybenzoic acid.

U.S. 3,864,499 discloses conventional dried casings treated with a high percentage of glycerin plasticizer. The glycerin containing casings, which are soaked prior to stuffing, are

German Patent Publication P 29 26 590 5 discloses high moisture casings which are sterilized by heat and stored in sterile packages. Such heating is energy intensive and is therefore undesirable. In addition the heating of such casings to sterilization temperatures can adversely affect the properties of the casing. The preserved, premoisturized casings disclosed above require high temperature sterilization or else require relatively high levels of polyols as plasticizer, and therefore, requirements for water as the primary plasticizer are reduced. Besides relying on glycerin, propylene glycol and other costly polyols for microbicidal and plasticizing properties, ready-to-stuff casings in many of the above instances are dried in energy intensive dryers or else require high temperature sterilization. Accordingly, there is a need for an improved ambient temperature preserved, premoisturized ready-to-stuff type sausage casing which can be stored indefinitely without developing molds, yeasts or bacteria wherein water performs as the sole or principal plasticizer.

BRIEF DESCRIPTION OF THE INVENTION

The present invention provides for novel premoisturized ready-to-stuff food casings and methods for their manufacture. "Ready-to-stuff" as used herein means having sufficient moisture to permit stuffing prior to shipment to the meat packing plant. Such "ready-to-stuff" casings contain at least 40 percent and preferably at least 55 percent water by dry weight of casing and also contain less than 15 and preferably less than 10, and more

19-0190630

specifically, from 0 to less than 10 percent polyol by weight of liquid in the casing. Humidification and plasticization are achieved by means of the water taken up by the casing during manufacture, thus, substantially eliminating or reducing the requirement for conventional chemical type plasticizers, e.g. glycerin, propylene glycol and other food grade polyols. The casings are preserved to inhibit development of molds, yeasts, and bacteria allowing storage for indefinite time periods. The humidified casings are preserved only with an effective amount of a high pH active antimycotic agent. The "effective amount" is an amount which will inhibit the development of a broad range of common molds without significantly affecting the surface degradation of products contained in the casing. The "effective amount" may go as low as a few parts per million and is usually less than 0.5 percent by weight of liquid in the casing. It is understood that inclusion of an effective amount of high pH active antimycotic excludes the presence of 15 percent or more polyol by weight of liquid in the casing. "High pH active" means that the antimycotic preservative is effective throughout the pH range of 5 to 9 at a concentration of less than 0.2 percent by weight of liquid in the casing. However, it is to be understood that "effective amount" is intended to include amounts of high pH active preservatives in excess of 0.2 percent by weight of liquid in the casing.

The premoisturized casings rely on water as the primary plasticizer, and in some instances the sole plasticizer, in

combination with minor amounts of a high pH active antimycotic agent as a preservative. The combination provides important benefits in terms of conservation of energy. That is, energy requirements customarily expended in drying food casings can be substantially reduced or even eliminated. Further economic benefits are also realized as a result of reduced requirements for more costly chemical type plasticizers, e.g. glycerin and other polyols.

The invention includes preserved, high moisture unreinforced and fibrous reinforced gel type casings, such as flat stock for large type stuffed meat products, like bolognas, and for use in conjunction with automatic stuffers etc. In the case of gel type premoisturized casings, all drying requirements may optionally be eliminated. The invention also includes such casings in prepackaged form.

DETAILED DESCRIPTION OF THE INVENTION

The present invention generally relates to premoisturized food casings, their methods of manufacture and more particularly, to ready-to-stuff meat or sausage casings prepared with sufficient moisture as to be readily stuffed with a food product without further moisture being added beforehand by the food processor. The casings are preserved with a sufficient amount of a high pH active non-polyol antimycotic agent, preferably an alkyl ester of p-hydroxybenzoic acid, to prevent the development of molds, and desirably other microorganisms such as yeasts and

bacteria, even during prolonged periods of storage.

The fibrous and non-fibrous reinforced ready-to-stuff casings of the present invention may be used for meat and sausage products like frankfurters, bologna, salami, deli-loaves, turkey rolls, hams, etc. Unlike conventional sausage casings supplied to meat processors in shirred strands and in relatively short flattened tubular lengths, which must first be soaked in water prior to stuffing, casings of the present invention contain sufficient moisture that soaking or other moisture addition processes need not be performed by food processors before stuffing. Thus, for purposes of the present invention, such expressions as "premoisturized" and "ready-to-stuff" are intended to mean food casings having sufficient water that food processors may omit the customary step of soaking the casings just prior to stuffing.

The moisture content of the casings is usually at least 40 percent by weight based on dry weight of casing. In most instances, the casings will be plasticized with from about 40 to about 240 percent by weight based on dry weight of casing. More preferably, the water content will range from about 55 to about 170 percent by weight based on dry casing.

Unlike other premoisturized ready-to-stuff casings, those of the present invention do not rely on polyols like glycerin and propylene glycol as plasticizers, nor as preservatives. The present invention contemplates embodiments whereby requirements for polyols for plasticizing and preserving casings can be

dramatically reduced and even totally eliminated. Instead, the premoisturized casings are plasticized with higher levels of water, such as previously described and other high pH active antimycotic agents are used instead of polyols. If polyols are present, they will be present in minor amounts, i.e. less than 15 percent and preferably less than 10 percent by weight of liquid in the casing.

This is a rather significant departure from prior art premoisturized and preserved casings, such as described in U.S. Patent 4,409,251, where ready-to-stuff type casings have at least 40 weight percent glycerin based on total weight of dry cellulose in the casing. British Patent Specification 1,584,435 actually describes the need for substantially greater amounts of polyol for the particular level of water used which imparts the desired flexibility and stuffing characteristics to the casing. Thus, it was surprising to find that high moisture levels can be maintained without accompanying higher levels of propylene glycol, glycerin and the like. Accordingly, the higher water levels of the subject casings not only provide economic benefits in terms of raw materials, but it was also found that the performance of the casing per se in terms of feed characteristics in stuffing equipment is also improved in many instances over other premoisturized, ready-to-stuff casings prepared with lower water contents and higher polyol loadings.

According to the method of the present invention the water imbibed by the casing during washing will plasticize the casing

and the prior art need for adding on polyol or drying the casings subsequently and then remoisturizing can be eliminated at significant cost savings.

In accordance with the present invention it has been surprisingly found that the casings can be preserved by adding on controlled amounts of high pH active antimycotic agents with little or no polyol. Examples of such antimycotic agents are 1,2 benzisothiazolin-3-one; 1,2 dibromo 2,4 dicyanobutane; natamycin and the alkyl esters of p-hydroxybenzoic acid. Antimycotic agents commonly used in the prior art which are free acids or acid salts are generally not effective throughout the pH range of 5 to 9 and are therefore generally not high pH active antimycotic agents in accordance with the present invention. Preferred high pH active antimycotic agents are the lower alkyl ($C_1 - C_7$) esters of p-hydroxybenzoic acid.

The antimycotic agent may be applied to the wet casing from an aqueous medium. The applied antimycotic agent may be on the surface or enter the casing. In either case the agent is considered to be "incorporated into the casing". In the case of alkyl esters of p-hydroxybenzoic acid the solution is usually substantially saturated with the ester with or without the benefit of accompanying surfactants or cosolvents. The objective, in either case, is to incorporate amounts of antimycotic agent into the casing sufficient to inhibit the development of molds and desirably also bacteria and yeasts during storage of the casing without altering normal shelf-life

of the meat product after the casing is stuffed.

In most instances, the antimycotic agent should be free or substantially free of acid groups or acid salts.

High pH active antimycotic agents are desirable because in accordance with the present invention, it has been found that storing casing at a low pH, e.g. below 5 is deleterious to the casing. Propionic and sorbic acids, for instance, at low pH over a period of time, i.e...during storage and shipment, may have a deleterious affect on the casing material resulting in a weakening and loss of wet strength, etc. and in addition are usually not high pH active. Furthermore, it has been found in accordance with the present invention that even if the casing is stored at a low pH, the pH tends to rise with time, possibly due to the reactivity of the -OH groups in the cellulose and starches from which many such casings are made. When the pH rises to pH 5 to 9, many common antimycotics tried in the prior art become ineffective, especially those antimycotics which have a high molecular weight percent of acid groups. Effective antimycotic agent compounds for use in the present invention usually contain less than 10 molecular weight percent acid groups, i.e. they are essentially free of such groups.

The concentration of antimycotic agent may be 50 ppm or lower, by weight of liquid in the casing. However, for the parabens (alkyl p-hydroxybenzoates) the preferred range is from about 100 to about 1100 ppm, and more optimally, from about 200 to about 500 ppm. At such concentrations the casings can be

stored and shipped over extended time periods without the development of microorganisms. Concentrations as high as 2000 ppm (0.2%) may be used. Even higher concentrations may be employed, but without added benefit, and there may be an added risk of diffusion into the meat product after stuffing which may mask the natural formation of slime or greening normally observed with deterioration and spoilage of meat products.

In the case of paraben esters, the effectiveness of the casings in resisting development of microorganisms may be influenced by the solubility of the particular ester in the treating bath from which it is applied. That is, the solubility of the alkyl esters of p-hydroxybenzoic acid in water is limited, e.g. 400 ppm at 25°C for the propyl ester; 150 ppm for the butyl ester and 1100 ppm for the ethyl ester. The preferred esters are therefore lower alkyl esters, e.g. methyl, ethyl, propyl, butyl, or n-heptyl.

In some instances, it was found that aqueous treating solutions containing propyl paraben prepared at room temperature did not appear to provide adequate microbicidal activity for the casing. Hence, the present invention contemplates the use of saturated solutions heated above ambient temperature conditions, i.e...above 25°C. For example, propyl paraben may be utilized in water where the solubility of the ester at 40°C increases to about 640 ppm. After the moisturized casings are treated in aqueous solutions of propyl paraben at elevated temperatures and cooled, some of the antimycotic agent imbibed may crystallize in-

situ and provide for continuous saturation of the liquid phase of the casing and protect the casing against development of microbes. Accordingly, such casings may be plasticized only with water and preserved with partially dispersed and partially dissolved paraben ester. The requirement for using heated saturated aqueous solutions for other lower alkyl esters, e.g. methyl and ethyl, may be omitted due to their more favorable solubility characteristics.

As an alternative preferred embodiment, it is sometimes advantageous to first dissolve the antimycotic agent in a cosolvent. Dissolution of certain lower alkyl esters of p-hydroxybenzoic acid, e.g., propyl paraben in an alcoholic cosolvent can improve overall microbiocidal activity. For example, only 0.04 grams of propyl paraben will dissolve in water (100 grams) at 25°C; whereas, 26 grams will dissolve in 100 grams of propylene glycol. Therefore, the paraben treating bath may be prepared by first dissolving the ester in an alcohol, such as propylene glycol. Other suitable food grade polyols may be used as alcoholic cosolvents. However, propyl paraben, for example, appears to have the most favorable solubility characteristics in propylene glycol. Ethanol may also be used. The parabens, which quickly dissolve in the co-solvent are then added to water normally without precipitation of the ester. The alcoholic cosolvents are generally employed in "ester solubilizing amounts," which for purposes of the immediate invention include quantities which aid in the dissolution of the alkyl esters of



p-hydroxybenzoic acid and exclude quantities which impart material antimycotic activity to the casing. Thus, baths for applying the antimycotic agent may contain, for example, from about 100 to 1500 ppm propyl paraben and from 0 to about 32 percent by weight of a cosolvent such as propylene glycol and more preferably from about 2 to about 25 percent by weight cosolvent. More preferably, aqueous application baths will contain from about 300 to about 1100 ppm propyl paraben and from 0 to about 20 weight percent propylene glycol cosolvent. The actual amount of cosolvent, if used, will usually be the least amount needed to presolubilize the paraben ester before incorporating into the aqueous application bath, which bath may be maintained at ambient or elevated temperatures. As previously indicated, the premoisturized fibrous casings may be free or substantially free of polyols, e.g., propylene glycol, ethanol and the like; however, when employed, the amount of cosolvent added on to the casings will be below 15 percent by weight, and more specifically below about 10 percent by weight. "Substantially free" of polyols means that the amount of polyol present does not materially change the antimycotic properties of the casing.

The casings contemplated herein are tubular food casings in the form of flat reelstock or individual shirred strands, and more particularly, fibrous reinforced and non-fibrous reinforced meat casings. Typically, casings are formed from cellulose, cellulose ethers, esters, collagen, polyvinyl alcohol, amylose,

high amylose starches, to name but a few. For example, casings prepared from regenerated cellulose, cellulose ethers, etc., can be made by processes such as the cuprammonium process, by denitration of cellulose nitrate, and preferably by the "viscose process". According to one embodiment of the present invention, a fibrous web consisting of cellulosic fibers, hemp, rayon, sisal or other fibrous materials may be coated with viscose by extrusion methods using known techniques. The coated web is then coagulated to effect regeneration of the cellulose by passing the extruded material into an aqueous bath containing, for example, sodium sulfate and sulfuric acid. The coagulation liquid is applied to convert the cellulose xanthate to cellulose. The regenerated casing is then washed in water to purify and remove chemicals to form a gel type casing having a high moisture content. The casing is then treated in the bath containing the antimycotic agent, as previously described, to preserve the casing. The casings prepared according to the foregoing method can be stored over prolonged time periods and supplied as flat reelstock to meat processors.

The high moisture gel type casings in the form of flat reelstock provide very smooth performance, for instance, in modern integrated shirr-stuff and clip type meat processing equipment without the need for further soaking prior to stuffing. Such machines perform the steps of first gathering or loosely shirring the ready-to-stuff casing on a stuffing horn which is subsequently indexed to a stuffing position. The casing is then

filled with a meat emulsion and closed by means of an automatic clipping or twisting mechanism. Equipment of this type is available under the designation Poly-Clip, a registered trademark of Niedecker GMBH of Frankfurt, West Germany. The casings of the present invention may operate smoothly in the equipment described in U.S. Patent 4,358,873. Pre-shirred strands of ready-to-stuff casings are also intended within the context of the present invention. Under such circumstances, some drying may be desirable for most efficient shirring operation. However, it is to be understood that even under those circumstances where the casings are subjected to a drying step the final elevated moisture content will be within the range described hereinabove.

Where a higher density shirring is desired, obviously further drying of the casing will be required in which case some glycerin can be added by conventional means to aid in plasticizing the casing and to avoid possible damage as a result of pinholing. Drying and the addition of glycerin may also be desirable in those instances where, for example, high temperature meat release or peeling aids are coated onto interior walls of casings to avoid removing meat with the casing when stripped by consumers. Drying may also be required in those instances where direct printing onto the finished casing is desired. It should be noted, however, that alternative type low temperature peeling aids, such as carboxy methyl cellulose may be substituted in place of high temperature release agents thereby avoiding the need for drying. Similarly, drying can also be eliminated by use

of printed outer packaging jackets for the stuffed meat products in place of direct printed casings. Alternatively, the fibrous web may be imprinted prior to coating with viscose. Likewise, drying and the addition of glycerin can be eliminated in most instances because flat reelstock is more desirable than high density shirred tubular casings for most ready-to-stuff applications. However, when drying is not eliminated casings according to the present invention are remoisturized to the above stated levels.

The following specific examples demonstrate the products and methods of the present invention. However, it is to be understood that these examples are for illustrative purposes only and do not purport to be wholly definitive as to conditions and scope.

EXAMPLE I

A clear synthetic small diameter fibrous sausage casing is prepared by forming a long fiber hemp paper into a continuous tube which is passed through an annular die where a viscose dope consisting of cellulose xanthate dissolved in caustic soda is coated on both the inner and outer sidewalls saturating the web with a matrix. The saturated fibrous tube is then regenerated in an aqueous coagulating bath containing sulfuric acid, ammonium sulfate and sodium sulfate, and rinsed in a series of aqueous wash tanks to remove chemical impurities. Instead of plasticizing in glycerin or adding propylene glycol, the casing is immersed in an aqueous preservative bath saturated with 1500

ppm of propyl paraben. The bath temperature is between 65 and 70°C. The residency time is two minutes. The casing is then reeled from the preservative bath, partially dried and analyzed. Propyl paraben content is determined by UV spectrophotometry by first extracting a sample with methanol and measuring absorbance at 295 nm after making the extract slightly basic. Moisture content is determined by toluene distillation by first reflexing the casing sample in toluene using a Dean-Stark Trap. The casing has a moisture content of 40 percent on an as is basis and about 525 ppm propyl paraben both on an as is basis.

Three 80 foot strands, prepared above, are inoculated with at least 5×10^4 spores of each of the following genera molds: Aspergillus, Penicillium, Cylindrocephalum, Fusidium, and Alternaria which were previously isolated from contaminated casings. A control casing is also prepared according to the above procedure except that it is not treated in the preservative bath containing the propyl paraben. The control is inoculated with spores from each of the same five molds. The humidified and inoculated strands, including the control, are placed in individual polyethylene bags and placed in a conditioning cabinet maintained at 85 percent relative humidity and a temperature of 30°C. The strands are maintained under these conditions for 40 consecutive days and then examined. The control strand which had not been treated in the preservative bath is observed to have heavy mold growth over the entire surface of the strand; whereas despite the heavy inoculation, one

of the test stands showed no detectable mold growth and the remaining two test strands showed only very slight growth.

EXAMPLE II

Premoisturized, ready-to-stuff fibrous cellulosic sausage casing is prepared following the procedure of Example I except the preservative bath is prepared with 900 ppm propyl paraben containing 85 percent water and 15 percent propylene glycol as a cosolvent. The propyl paraben is first dissolved in the propylene glycol and then added to the water. The bath temperature is maintained at 60°C. All the propyl paraben remains in solution. The fibrous casing is immersed in the bath for two minutes and partially dried by conventional means to provide a casing with about 300 ppm propyl paraben on an as is basis, 5 percent propylene glycol by weight of liquid in the casing and a moisture content of about 50 percent on an as is basis. The casing is then shirred into individual strands of approximately 14 inches using conventional methods. In order to test the storagability of the strands three are inoculated with at least 5×10^4 spores/strand from the molds described in Example I and placed in individual polyethylene bags and stored according to the procedure of Example I. A control strand not treated in the preservative bath is also inoculated and tested. Two of the test strands have no observable mold growth. The third strand has only slight growth. The control casing shows appreciable contamination with visible mold.

Generally, fibrous casing under good practice handling conditions will have a spore contamination on the casing surface of less than one-half spore per square inch. Accordingly, the spore loading conditions of Examples I and II far exceed those encountered under typical packing house conditions.

EXAMPLE III

Large diameter gel type regenerated cellulose casing is prepared by the well known viscose process. Instead of plasticizing in an aqueous glycerin bath and drying the casing after being washed in a water bath, the casing is treated in a preservative bath at 60°C for two minutes containing 900 ppm propyl paraben, 15 percent propylene glycol cosolvent and 85 percent water. The casing is analyzed and found to contain 219.5 percent water, 10.56 percent propylene glycol and 275 ppm propyl paraben all by dry weight. The premoisturized and preserved casing is wound on a reel and mounted on a Niedecker TCA Poly-Clip automatic stuffing machine. Bologna emulsion is stuffed in 500 feet of casing without casing breakage. The casing feeds smoothly through the shirring, stuffing and clipping cycles of the machine. Size control compares favorably with regular casing which is soaked in hot water prior to stuffing.

While the invention has been described in conjunction with specific examples thereof, this is illustrative only. Accordingly, many alternatives, modifications and variations will be apparent to persons skilled in the art in light of the

425-010190630
-24-

foregoing description, and it is therefore intended to embrace all such alternatives, modifications and variations as to fall within the spirit and broad scope of the appended claims.

1 What is claimed is:

1. A method of preserving a ready-to-stuff premoisturized food casing which comprises incorporating an effective
5 amount of a high pH active antimycotic agent into said casing.
2. The method of Claim 1 wherein the finished casing contains less than 10 percent polyol by weight of liquid
10 in the casing, and includes the step of packaging the casing.
3. The method of Claim 1 wherein the antimycotic agent is an alkyl ester of p-hydroxybenzoic acid and the casing
15 comprises from about 40 to about 240 weight percent water based on dry casing and from 100 to 1100 ppm of said ester.
4. The method of Claim 3 wherein the casing comprises from
20 about 55 to about 170 weight percent water based on dry casing and from about 200 to about 500 ppm of the p-hydroxybenzoic acid ester.
5. The method of Claim 1 wherein the casing is a fibrous
25 reinforced type casing or non-fibrous reinforced casing.
6. The method of Claim 3 including the step of first forming a preservative solution which comprises a saturated aqueous solution of the p-hydroxybenzoic acid ester.
30
7. The method of Claim 3 wherein the solution is an aqueous solution comprising from about 100 to about 1500 ppm of the p-hydroxybenzoic ester.
- 35 8. The method of Claim 6 or 7 including the step of heating the solution to above ambient temperature conditions.
9. The method of Claim 3 including the step of dissolving

- 1 the p-hydroxybenzoic acid ester in a cosolvent and adding the resulting cosolvent solution to water to form an aqueous preservative solution.
- 5 10. The method of Claim 9 wherein the cosolvent is an alcohol employed in an ester solubilizing amount, preferably propylene glycol, ethanol or mixtures thereof, especially propylene glycol.
- 10 11. The method of Claim 10 wherein the p-hydroxybenzoic acid ester is a member selected from the group consisting of methyl, ethyl, propyl, butyl, and n-heptyl, preferably propyl p-hydroxybenzoate.
- 15 12. The method of Claim 11 wherein the casing comprises from about 100 to about 500 ppm of the propyl p-hydroxybenzoate.
- 20 13. The method of Claim 1 wherein the casing is substantially free of polyol.
- 25 14. A method of inhibiting development of microorganisms in premoisturized, ready-to-stuff food casings having reduced drying requirements which comprises the steps of providing a casing comprising at least about 40 weight percent water based on dry casing, and contacting the casing with a preservative solution comprising a C₁ to a C₇ alkyl ester of p-hydroxybenzoic acid in a sufficient amount to impart to said casing from about 30 100 to about 1100 ppm of the ester, said ester being dissolved in an aqueous solution contacting from 0 to about 32 percent by weight of a cosolvent, and packaging said casing.
- 35 15. The method of Claim 14 wherein the casing is a fibrous reinforced type casing or non-fibrous type casing.
16. The method of Claim 15 wherein the water content of the

1 casing is from about 55 to 170 percent by weight based
on dry casing.

17. The method of Claim 16 wherein the cosolvent is an alco-
5 hol and the p-hydroxybenzoic acid ester is present in
the preservative solution in an amount sufficient to
impart from about 200 to about 500 ppm to the casing,
said cosolvent being present in solution in an amount
from about 2 to about 25 percent by weight, preferably
10 the alcoholic cosolvent is propylene glycol, ethanol
or mixtures thereof, and especially the alcoholic cosol-
vent is propylene glycol and especially the ester is
propyl p-hydroxybenzoate.

15 18. The method of Claim 14 wherein the casing is substanti-
ally free of polyol.

19. A method for making plasticized, storable food casings
having sufficient moisture content that no additional
20 moisture is required prior to stuffing, which comprises:

- a) forming a film forming polymer into a length of tubu-
lar material;
- 25 b) regenerating the tubular material in a coagulating
bath;
- c) washing and plasticizing the casing with water;
- 30 d) preserving the casing by contacting it with an aque-
ous solution comprising a high pH active antimycotic
agent substantially free of acid groups to impart
an effective amount into the casing, said solution
including 0 to about 32 percent by weight of an alco-
35 holic cosolvent; and
- e) packaging the casings.

- 1 20. The method of Claim 19 wherein the antimycotic agent
is an alkyl ester of p-hydroxybenzoic acid, the film
forming polymer is cellulose and the water content of
the casing is from about 40 to about 240 percent by
5 weight based on dry casing.
21. The method of Claim 20 including the step of reducing
the water content by drying.
- 10 22. The method of Claim 21 wherein the preserved casing has
a moisture content of between about 55 and about 170
weight percent based on dry cellulose.
23. The method of Claim 20 wherein the casing is substanti-
15 ally free of glycerin and propylene glycol.
24. The method of Claim 21 wherein the moisture content of
the casing is at a level as to permit shirring of said
casing.
- 20 25. The method of Claim 21 wherein the alkyl ester of p-hy-
droxybenzoic acid is methyl, ethyl, propyl, butyl or
n-heptyl and the alcoholic cosolvent is selected from
the group consisting of propylene glycol, ethanol and
25 mixtures thereof.
26. The method fo Claim 25 wherein the preservative solution
imparts to the casing from about 50 to about 500 ppm
of propyl p-hydroxybenzoate.
- 30 27. A packaged premoisturized food casing suitable for stuf-
fing without further moisture being added thereto prior
to said stuffing, comprising at least about 40 weight
percent water based on dry casing and an effective
35 amount of high pH active antimycotic agent substantially
free of acid groups, preferably the water content being
from about 40 to about 240 weight percent based on dry
casing and the antimycotic agent being an alkyl ester

1 of p-hydroxybenzoic acid present in an amount from about
 50 to about 1100 ppm, said casing having less than 10
 percent polyol by weight of liquid in the casing, espe-
 5 cially the casing being a fibrous reinforced cellulosic
 casing having a water content of between about 55 and
 about 170 weight percent moisture based on dry weight
 of cellulose and from about 50 to about 1100 ppm of a
 lower alkyl ester of p-hydroxybenzoic acid and from 0
 to less than 15 percent by weight of an alcohol selected
 10 from propylene glycol, ethanol and mixtures thereof.

28. The casing of Claim 27 including a fibrous web coated
 with a polymer comprising regenerated cellulose, amylose
 or an amylose starch.

15

29. The casing of Claim 28, substantially free of chemical
 type plasticizers.

30. The casing of Claim 27 wherein the polyol is selected
 20 from propylene glycol, glycerin, ethanol and mixtures
 thereof.

31. The cellulosic casing of Claim 27 comprising from about
 200 to about 500 ppm of propyl p-hydroxybenzoate and
 25 from about 1 to 10 weight percent of propylene glycol
 based on dry weight of cellulose.

32. The cellulose casing of Claim 27 wherein the casing is
 substantially free of glycerin and propylene glycol.

30

33. A food casing containing sufficient moisture to permit
 stuffing without further moisture addition, said casing
 comprising an effective amount of a high pH active anti-
 mycotic agent, said moisture being present in an amount
 35 of from 40 to 240 percent by dry weight of casing and
 said antimycotic agent being present in an amount suffi-
 cient to impart antimycotic properties to said casing
 without significantly impeding visual evidence of spoil-

- 1 age or deterioration of meat which is stuffed into the
casing, said casing containing less than 15 percent po-
lyol by weight of liquid in the casing, preferably the
antimycotic agent being in alkyl ester of p-hydroxyben-
5 zoic acid, the casing containing less than 10 percent
polyol by weight of liquid in the casing and the casing
being a fibrous food casing.
34. The casing of Claim 33 wherein the casing is substantial-
10 ly free from glycerin.
35. A stuffed meat product comprising a food casing and meat
containing therein said food casing comprising a fibrous
15 casing having a pre-stuffing moisture content sufficient
to permit stuffing without further moisture being added
thereto prior to such stuffing, said casing comprising
an effective amount of a high pH active antimycotic
agent from 40 to 240 weight percent water based on dry
20 weight of casing, the antimycotic agent being present
in a sufficient amount to impart antimycotic properties
to the casing, but without impeding evidence of spoilage
or deterioration of the meat product, said casing con-
taining less than 15 percent polyol by weight of liquid
25 in the casing, preferably the antimycotic agent being
an alkyl ester of p-hydroxybenzoic acid and the casing
containing less than 10 percent polyol by weight of li-
quid in the casing.
- 30 36. The meat product of Claim 35 stuffed in a cellulosic
casing having a pre-stuffing moisture content ranging
from about 55 to about 170 weight percent water based
on weight of the dry weight of fibrous material and from
about 200 to about 500 ppm of the p-hydroxybenzoic ester.
35
37. The meat product of Claim 35 or 36 wherein the casing
is substantially free of glycerin.



European Patent
Office

EUROPEAN SEARCH REPORT

0190630

Application number

EP 86 10 1028

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl. 4)
D, Y	GB-A-1 584 435 (UCC) * Claims 1-27 *	1-37	A 22 C 13/00
D, Y	US-A-3 864 499 (A.F. TURBAK) * Claims 1-22 *	1-37	
Y	GB-A-2 105 170 (UCC) * Claims 1-16 *	1-37	
D, A	US-A-3 617 312 (H.J. ROSE) * Claim 1 *	1	
			TECHNICAL FIELDS SEARCHED (Int. Cl. 4)
			A 22 C
The present search report has been drawn up for all claims			
Place of search THE HAGUE		Date of completion of the search 22-05-1986	Examiner PERMENTIER W.A.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document		T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document	

EPO Form 1503 03 82

THIS PAGE BLANK (CONT)

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: _____**

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.

THIS PAGE BLANK (USPTO)